

v02.0209

# GaAs HEMT MMIC LOW NOISE AMPLIFIER, 14 - 27 GHz

## **Typical Applications**

This HMC-ALH476 is ideal for:

- · Point-to-Point Radios
- · Point-to-Multi-Point Radios
- · Military & Space
- Test Instrumentation


#### **Features**

Noise Figure: < 2 dB @ 20 GHz

Gain: 20 dB

P1dB Output Power: +14 dBm Supply Voltage: +4V @ 90 mA Die Size: 2.25 x 1.58 x 0.1 mm

## **Functional Diagram**



## General Description

The HMC-ALH476 is a GaAs MMIC HEMT Low Noise Wideband Amplifier die which operates between 14 and 27 GHz. The amplifier provides 20 dB of gain, 2 dB noise figure and +14 dBm of output power at 1 dB gain compression while requiring only 90 mA from a +4V supply voltage. The HMC-ALH476 amplifier is ideal for integration into Multi-Chip-Modules (MCMs) due to its small size.

## Electrical Specifications, $T_{A} = +25^{\circ}$ C, Vdd = +4V

Parameter	Min.	Тур.	Max.	Min.	Тур.	Max.	Units
Frequency Range		14 - 18			18 - 27		GHz
Gain	18	20		18	20		dB
Gain Variation over Temperature		0.02			0.02		dB/°C
Noise Figure		2.5	3		2	2.6	dB
Input Return Loss		16			17		dB
Output Return Loss		18			20		dB
Output Power for 1 dB Compression		14			14		dBm
Supply Current (Idd) (Vdd = 4V, Vgg = -0.3V Typ.)		90			90		mA


<sup>\*</sup>Unless otherwise indicated, all measurements are from probed die




v02.0209

# GaAs HEMT MMIC LOW NOISE AMPLIFIER, 14 - 27 GHz


## Linear Gain vs. Frequency




## Noise Figure vs. Frequency



## Input Return Loss vs. Frequency



## **Output Return Loss vs. Frequency**






# GaAs HEMT MMIC LOW NOISE AMPLIFIER, 14 - 27 GHz

## **Absolute Maximum Ratings**

Drain Bias Voltage	+4.5V
RF Input Power	-2 dBm
Gate Bias Voltage	-1 to 0.3V
Thermal Resistance (Channel to die bottom)	44.6 °C/W
Channel Temperature	180 °C
Storage Temperature	-65 to +150 °C
Operating Temperature	-55 to +85 °C



## **Outline Drawing**



# Die Packaging Information [1]

Standard	Alternate	
GP-1 (Gel Pack)	[2]	

[1] Refer to the "Packaging Information" section for die packaging dimensions.

[2] For alternate packaging information contact Hittite Microwave Corporation.

#### NOTES

- 1. ALL DIMENSIONS ARE IN INCHES [MM].
- 2. TYPICAL BOND PAD IS .004" SQUARE.
- 3. BACKSIDE METALLIZATION: GOLD.
- 4. BACKSIDE METAL IS GROUND.
- 5. BOND PAD METALLIZATION: GOLD.
- 6. CONNECTION NOT REQUIRED FOR UNLABELED BOND PADS.
- 7. OVERALL DIE SIZE ±.002"

Information furnished by Analog Devices is believed to be accurate and reliable. However, no responsibility is assumed by Analog Devices for its use, nor for any infringements of patents or other rights of third parties that may result from its use. Specifications subject to change without notice. No license is granted by implication or otherwise under any patent or patent rights of Analog Devices. Trademarks and registered trademarks are the property of their respective owners.



v02.0209

# GaAs HEMT MMIC LOW NOISE AMPLIFIER, 14 - 27 GHz


# **Pad Descriptions**

Pad Number	Function	Description	Interface Schematic	
1	RFIN	This pad is AC coupled and matched to 50 Ohms.	RFIN ○──	
2, 6	Vdd	Power Supply Voltage for the amplifier. See assembly for required external components.	Vdd O—	
3, 5	Vgg	Gate control for amplifier. Please follow "MMIC Amplifier Biasing Procedure" application note. See assembly for required external components.	Vgg O	
4	RFOUT	This pad is AC coupled and matched to 50 Ohms.	—   —○ RFOUT	
Die bottom	GND	Die bottom must be connected to RF/DC ground.	⊖ GND —	



# GaAs HEMT MMIC LOW NOISE AMPLIFIER, 14 - 27 GHz

## **Assembly Diagram**



v02.0209

- Note 1: Bypass caps should be 100 pF (approximately) ceramic (single-layer) placed no farther than 30 mils from the amplifier.
- Note 2: Best performance obtained from use of <10 mil (long) by 3 by 0.5mil ribbons on input and output.
- Note 3: Biasable from either side.

Wire Bond



v02.0209

# GaAs HEMT MMIC LOW NOISE AMPLIFIER, 14 - 27 GHz

## Mounting & Bonding Techniques for Millimeterwave GaAs MMICs

The die should be attached directly to the ground plane eutectically or with conductive epoxy (see HMC general Handling, Mounting, Bonding Note).

50 Ohm Microstrip transmission lines on 0.127mm (5 mil) thick alumina thin film substrates are recommended for bringing RF to and from the chip (Figure 1). If 0.254mm (10 mil) thick alumina thin film substrates must be used, the die should be raised 0.150mm (6 mils) so that the surface of the die is coplanar with the surface of the substrate. One way to accomplish this is to attach the 0.102mm (4 mil) thick die to a 0.150mm (6 mil) thick molybdenum heat spreader (moly-tab) which is then attached to the ground plane (Figure 2).

Microstrip substrates should be placed as close to the die as possible in order to minimize bond wire length. Typical die-to-substrate spacing is 0.076mm to 0.152 mm (3 to 6 mils).

# 0.076mm (0.003") RF Ground Plane 0.127mm (0.005") Thick Alumina Thin Film Substrate Figure 1.

0.102mm (0.004") Thick GaAs MMIC

#### **Handling Precautions**


Follow these precautions to avoid permanent damage.

**Storage:** All bare die are placed in either Waffle or Gel based ESD protective containers, and then sealed in an ESD protective bag for shipment. Once the sealed ESD protective bag has been opened, all die should be stored in a dry nitrogen environment.

**Cleanliness:** Handle the chips in a clean environment. DO NOT attempt to clean the chip using liquid cleaning systems.

Static Sensitivity: Follow ESD precautions to protect against ESD strikes.

**Transients:** Suppress instrument and bias supply transients while bias is applied. Use shielded signal and bias cables to minimize inductive pick-up.



**General Handling:** Handle the chip along the edges with a vacuum collet or with a sharp pair of bent tweezers. The surface of the chip has fragile air bridges and should not be touched with vacuum collet, tweezers, or fingers.

#### Mounting

The chip is back-metallized and can be die mounted with AuSn eutectic preforms or with electrically conductive epoxy. The mounting surface should be clean and flat.

Eutectic Die Attach: A 80/20 gold tin preform is recommended with a work surface temperature of 255 °C and a tool temperature of 265 °C. When hot 90/10 nitrogen/hydrogen gas is applied, tool tip temperature should be 290 °C. DO NOT expose the chip to a temperature greater than 320 °C for more than 20 seconds. No more than 3 seconds of scrubbing should be required for attachment.

Epoxy Die Attach: Apply a minimum amount of epoxy to the mounting surface so that a thin epoxy fillet is observed around the perimeter of the chip once it is placed into position. Cure epoxy per the manufacturer's schedule.

#### Wire Bonding

RF bonds made with 0.003" x 0.0005" ribbon are recommended. These bonds should be thermosonically bonded with a force of 40-60 grams. DC bonds of 0.001" (0.025 mm) diameter, thermosonically bonded, are recommended. Ball bonds should be made with a force of 40-50 grams and wedge bonds at 18-22 grams. All bonds should be made with a nominal stage temperature of 150 °C. A minimum amount of ultrasonic energy should be applied to achieve reliable bonds. All bonds should be as short as possible, less than 12 mils (0.31 mm).