






Applications	 Commercial Grade
Feature	 No Directivity
	 Multilayer
	 Non-Mag Core Non-Magnetic Core (Dielectric Ceramic)
	High Self Resonant Frequency
Series Type	MLK
Status	 EOL announced
	Recommended Alternate Part No. : MLG0603S6N8JT000 (Interchangeability is not guaranteed.)
	Discontinue Issue Date : May.24, 2021
	Last Purchase Order Date : Mar.31, 2026
Brand	Last Shipment Date : Jun.30, 2026
	TDK







Size	
Length(L)	0.60mm ±0.03mm
Width(W)	0.30mm ±0.03mm
Thickness Height	0.30mm ±0.03mm
Recommended Land Pattern (A)	0.25mm Nom.
Recommended Land Pattern (B)	0.30mm Nom.
Recommended Land Pattern (C)	0.30mm Nom.

Electrical Characteristics	
Inductance	6.8nH ±5% at 100MHz
Rated Current	200mA
DC Resistance [Typ.]	340mΩ
DC Resistance [Max.]	650mΩ
Self Resonant Frequency [Min.]	6GHz
Self Resonant Frequency [Typ.]	8.1GHz
Q [Min.]	6 at 300MHz
Q [Typ.]	8 at 300MHz

Other	
Operating Temp. Range (Including Self-Temp. Rise)	-55 to 125°C
Soldering Method	Reflow
	Iron Soldering
AEC-Q200	NO
Packing	Punched (Paper)Taping [180mm Reel, Tape width 8mm]
Package Quantity	15000pcs
Weight	0.0002g

* Dimensions are for reference only and show exemplary products.
! This PDF document was created based on the data listed on the TDK Corporation website.
! All specifications are subject to change without notice.

Characteristic Graphs(This is reference data, and does not guarantee the products characteristics.)



Associated Images

