B66393G0000X197

磁芯形状	E (EE)
特点	Low Loss
材料名称	Mn-Zn
铁氧体材料	N97
状态	量产体制



	尺寸
Size (IEC 62317) AxBxC	E 16/6/5
其他详细信息	请参照规格书

Core Factor	
Effective Cross-Sectional Area	
Effective Magnetic Path Length	
Effective Core Volume	
AL Value / (nH / N²)	1250 ±25%
铁心损耗 / (W / set) [Max.]	
Air Gap	0 mm
重量	

电气特性(材料)		
初始磁导率 μi	2300 Nom.	
饱和磁通密度 Bs / mT	410 (100° C)	
居里温度 Tc [Min.]	230° C	
铁心损耗 / (kW / m³) [Max.]	300	


[!] Images are for reference only and show exemplary products.

[!] This PDF document was created based on the data listed on the TDK Corporation website.

 $^{! \ \}mbox{All specifications}$ are subject to change without notice.

B66393G0000X197

Associated Images



[!] Images are for reference only and show exemplary products.

[!] This PDF document was created based on the data listed on the TDK Corporation website.

 $^{!\ \}mbox{\em All}$ specifications are subject to change without notice.