

# 铁氧体磁芯

PC95PQ35/35Z-12

RoHS Pb Free

磁芯形状	PQ(PQ)
特点	<b>Low Temp Coef</b> Low temperature coefficient
	<b>Sw Power</b> For Switching Power Supplies
材料名称	Mn-Zn
铁氧体材料	PC95
状态	量产体制



## 尺寸

Size (IEC 62317) AxBxC PQ35/35

其他详细信息 [请参照目录](#)

## 电气特性

Core Factor	0.448mm <sup>-1</sup>
Effective Cross-Sectional Area	196mm <sup>2</sup>
Effective Magnetic Path Length	87.9mm
Effective Core Volume	17300mm <sup>3</sup>
AL Value / (nH / N <sup>2</sup> )	7320 ±25% (1kHz, 0.5mA, 100Ts)
铁心损耗 / (W / set) [Max.]	5.98 (200mT, 100kHz, 80° C)
Air Gap	0 mm
重量	73g

## 电气特性 (材料)

初始磁导率 $\mu_i$	3300 ±25%
饱和磁通密度 $B_s$ / mT	410 (1194A/m, 100° C)
居里温度 $T_c$ [Min.]	215° C
铁心损耗 / (kW / m <sup>3</sup> ) [Max.]	290

! Images are for reference only and show exemplary products.

! This PDF document was created based on the data listed on the TDK Corporation website.

! All specifications are subject to change without notice.